

Summary|Sheets

Material	Layer	Resin	Norm EN 60893	Temperature Resistance	Density	Mechanical Strenght			E-Modulus	Dielectic Strenght vertically	Dielectric Strenght parallel	Surface Resistance	Tracking Resistance
						MPa Tension	MPa Compression	Mpa Bending					
Krüpax 10-T	Paper	Phenol	PF CP 201	120	1,2	120	150	150	7.000	15	15	10 ⁸	100
Krüpax 15-T	Paper	Phenol	PF CP 202	120	1,2	100	150	130	7.000	40	40	10 ⁹	100
Krüpax 28-T	Paper	Phenol	PF CP 204	120	1,2	70	120	80	7.000	30	25	10 ¹⁰	100
Krüpax 30-T	Paper	Phenol	PF CP 204	120	1,2	70	100	80	7.000	25	20	5x10 ¹⁰	100
Krütex 100-T	Cotton, fine	Phenol	PF CC 201	120	1,4	80	170	130	7.000	5	8	10 ⁸	100
Krütex 102-T	Cotton, extra fine	Phenol	PF CC 203	120	1,4	100	170	150	7.000	5	8	10 ⁸	100
Krülit 700-T	Glass Fabric	Epoxy	EP GC 201	130	1,8	300	270	400	20.000	46	42	10 ¹¹	200
Krülit 704-T	Glass Fabric	Epoxy	EP GC 202	120	1,8	300	260	400	20.000	46	42	10 ¹¹	200
Krülit 750-T	Glass Fabric	Epoxy	EP GC 203	155	1,8	290	290	430	20.000	50	50	10 ¹¹	600
Krülit 750-TH	Glass Fabric	Epoxy	EP GC 303	180	1,8	290	290	430	20.000	50	50	10 ¹¹	600
Krülit 800-T	Glass Fabric	Silikone	SI GC 202	180	1,8	90	50	125	13.000	20	25	10 ¹⁰	440
Krülit 850-T	Glas-Roving	Epoxy	EP GC 205	155	1,8	310	300	350	22.000	54	48	10 ¹⁰	600

The above information is given to the best of our knowledge. In case of doubt, it is recommended to check the material for possible use.
The stated values are minimum values!

Krüger & Sohn GmbH
Robert-Bosch-Straße 1-3
D-84030 Landshut
www.kruegersohn.de